



Styron A-TECH 1115 PSAI



STYRON™ A-TECH™ 1115 advanced technology polystyrene resin is a high gloss, high-impact resin for injection molding and extrusion thermoforming applications.

MAIN CHARACTERISTICS

Easy Processing; High Gloss; High Impact; Consistent Colorability; FDA Compliant¹

APPLICATIONS

Custom High Gloss Extruded Sheet; Opaque Injection Molded Parts; Refrigeration Accessories; Small Appliances; Electric Lawn and Garden Equipment; Toys; Remote Controls

Propriedades ²	Test Method		S.I		English		Método ASTM	
	ISO	ASTM	Value	Unit	Value	Unit	Value	Unit
Physical								
Melt flow rate (200°C/5 Kg)	1133/8	D 1238	2.8		2.8	g/10 min	2.8	g/10 min
Specific Gravity	1183	D 792	1.03	g/10 min	1.03		1.03	
Linear thermal Expansion (10-5)	11359	D 696	8.1		4.5	in/in/°F	8.1	cm/cm ^o C
Mold Shrinkage		D 955	0.003 0.007	cm/cm ^o C	0.003 0.007	in/in	0.003 0.007	cm/cm
Optical								
60° Gardner Gloss		D 523						
Injection Molded			92	%	92	%	92	%
Termoformed			80	%	80	%	80	%
Thermal								
Vicat Softening Temperature 120°C/hr, 1 kg)	306A	D 1525-B						
Deflection Temperature Under Load (Injection molded) @ 0.45 MPa (66 psi), Unannealed @ 1.8 MPa (264 psi), Unannealed	76A	D 648	84 71	°C °C	183 160	°F °F	84 71	°C °C
Injection Molded Mechanical Properties								
Impact Strength:								
Notched Izod 12.7x3.2 mm (0.5x.125 in) specimen @ 23°C (73°F) @ -18°C (0°F)	180/4A	D256	224 85	J/m J/m	4.2 1.6	ft-lb/in ft-lb/in	23 86	kg-cm/cm kg-cm/cm
Gardner Impact @ 23°C (73°F)		D3029	37	J	320	in-lb	367	cm-kg
Tensile Properties 12.7x3.2 mm (0.5x0.125 in) specimen:								
Yield Tensile Strength 5mm/min (0.2 in/min) rate	527	D 638	21	MPa	3000	psi	211	kg /cm ²
Ultimate Tensile Strength 5mm/min (0.2 in/min) rate	527	D 638	18	MPa	2570	psi	181	kg /cm ²
Ultimate Elongation 5mm/min (0.2 in/min) rate	527	D 638	55	%	55	%	55	%
Tensile Modulus 5mm/min (0.2 in/min) rate	527	D 638	1827	MPa	265,000	psi	18630	kg /cm ²
Flexural Properties 1.3 mm/min (0.05 in/min) rate								
Flexural Strength (3-point)	178	D 790	44	MPa	6400	psi	450	kg /cm ²
Flexural Modulus (3-point)	178	D 790	2089	MPa	303,000	psi	21300	kg /cm ²
Flammability Properties³								
UL 94 Classification: @1.5 mm (0.06 in) thickness			HB		HB		HB	

¹When used unmodified for the manufacture of food contact articles, STYRON A-TECH 1115 will comply with Food Additive Regulations 21 CFR 177.1640 under the U.S. Food, Drug and Cosmetic Act. Such uses are subject to good manufacturing practices and any other limitations which are part of the statute or regulations. These should be consulted for complete details.

²Typical properties, not to be considered as specification limits.

³This numerical flame-spread rating is not intended to reflect hazards presented by material under actual fire conditions.



Styron A-TECH 1115
PSAI



PRODUCT STEWARDSHIP

The Dow Chemical Company and its subsidiaries (Dow) has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

CUSTOMER NOTICE

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

DOW MEDICAL APPLICATION POLICY

Dow will not knowingly sell or sample any product or service (“Product”) into any commercial or developmental application that is intended for:

- a. permanent (Long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours (except 30 days for PELLETHANE™ polyurethane elastomers);
- b. use in cardiac prosthetic devices regardless of the length of time involved; (Cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices);
- c. use as a critical component in medical devices that support or sustain human life; or
- d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Additionally, all Products intended for use in pharmaceutical applications, other than pharmaceutical packaging, must pass the current Pharmaceutical Liability Guidelines.

- For the products sold by the Plastics Portfolio, new business opportunities require a business assessment prior to sale or sampling of Dow products.
- Authorized distributors and resellers will adhere to this medical policy.
- The Dow Chemical Company does not endorse or claim suitability of their products for specific medical applications.
- It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS**

DISCLAIMER

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer’s use and for ensuring that the Customer’s workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as “experimental” or “developmental”: (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; and (3) there is greater potential for Dow to change specifications and/or discontinue production.